



Product Model

Firefoam B2 Handheld

EverBuild Firefoam B2 Handheld is a quick setting one part polyurethane foam with fire resistance properties. The foam expands on application to up to 50 times its original volume and meets the requirements of DIN 4102 Part 1 for Construction Materials and BS476 Part 20. Fire rated up to 2 hours in certain joint configurations. Copies of the independent test certificate, Warrington fire report number 160902 are available on request. Once cured, the foam can be cut, sawn or plastered over after only one hour providing the working temperatures (can and surfaces) are between +5 to +25°C, ideally 20°C.

Product Code	Pack Size	Box Qty
B2FIREHAND	750ML	12

Technical data supplied by the manufacturer



Benefits

- High degree of fire rating: slows down the passage of flames and smoke in comparison to standard B3 grades
- Quick setting - can be cut, sawn or plastered in 1 hour.
- Economical in use - expands up to 50 times its original volume.
- Fills irregular and broad gaps where most conventional fillers would fail.
- Possesses insulating and sound deadening properties.

Limitations

- Carefully read instructions and text in warning box before use.
- Not suitable for use with P35 gun. Use P20 or P65.
- Do not over pressurize container.
- Always apply above 5°C.
- Clean spills immediately with Everflex Foam Cleaner.

Surface Preparation

Ensure all surfaces are clean, sound and free from dust and loose particles. **Moisten surfaces to be sealed with water. This assists the curing process.**

Areas for Use

Filling

- Gaps around pipe entries through fire rated walls
- To provide a fire rated seal around window and door frames
- Electrical wire chasing prior to plastering, where a fire rating is required.
- Deep joints prior to applying sealant or plaster
- Irregular gaps in stone, brick, concrete or plaster

Fixing

- Door frames
- Timber structures
- Windowsills and thresholds.
- Window frames

Insulating

- Behind cladding to exterior walls.
- Behind soffit and barge boards
- In automotive applications.

When used as part of a fire rated joint, use in conjunction with Everflex Firemate intumescent sealant for maximum fire rating.

Solutions, Service and Supplies to the Trade

Springhead Enterprise Park, Springhead Road, Northfleet, Kent DA11 8HJ
 T 01322 274226 F 01322 278178 E sales@fixmart.co.uk www.fixmart.co.uk



Application

Always wear protective gloves.

Shake can well before use (about 20 times).

Carefully fix nozzle. Do not overtighten or force.

Always use can upside down.

Only partially fill cavities, as the foam will expand to fill the remaining space. Any excess foam can be removed whilst still wet with **Everflex Foam Cleaner**. Cured foam must be removed mechanically. Always remove nozzle from can and clean immediately after use with **Everflex Foam Cleaner**. When used for fixing doorframes, supports must be used until the foam is fully cured.

Health & Safety

Consult MSDS for full list of hazards

Shelf Life

12 months in original containers at stated storage temperatures.

Please note

When transported in cars, keep in boot, out of direct sunlight. When removing cured foam from skin, take care not to damage with abrasives. Grease skin with body lotion or similar.

Important – Re-use is only possible by cleaning the nozzle and valve tip with **Everbuild Dual Purpose Foam Cleaner** before the foam has cured. Do not push any object into the valve as the contents may explode.

Storage

Store upright between 20 and 25°C Pressurized container. Protect from sunlight and do not expose to temperatures above 50°C. Do not pierce or burn the can even after use. Store as flammable liquid. Note: Elevated temperatures will reduce shelf life dramatically.

Expansion	37 litres (750ml can)
Cell Structure	Medium fine
Tack Free	Approx. 8 minutes
Cuttable	20 mins to 1 hour depending on bead dimensions.
Full Load Bearing Stability	App, 12 hours (20mm bead)
Working Temps	5°C - 25°C. (Optimum 20°C)
Tensile Strength	18N/cm ² (DIN 53455)
Elongation At Tension	30% (DIN 53455)
Shear Strength	8N/cm ² (DIN 53422)
Flexural Strength	20N/cm ² (DIN 53423)
Compressive Strength	5N/cm ² (DIN 53421) at 10% stress.
Water Absorption	0.3 Vol % (DIN 53428)
Thermal Conductivity	0.04 W/Mk (DIN 52612)
Temp Res Of Cured Bead	Long Term: -40 - +100°C Short Term: -40 - +130°C
Building Material Class	B2 (DIN 4102, Part 1)

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.

Solutions, Service and Supplies to the Trade

Springhead Enterprise Park, Springhead Road, Northfleet, Kent DA11 8HJ

T 01322 274226 F 01322 278178 E sales@fixmart.co.uk www.fixmart.co.uk